


IN THE UNITED STATES PATENT AND TRADEMARK OFFICE  
REQUEST FOR FILING APPLICATION UNDER 37 CFR 53(b)  
WITHOUT FILING FEE OR EXECUTED INVENTOR'S DECLARATION



Assistant Commissioner for Patents  
Washington, DC 20231

Atty. Dkt. 839-750

Date: April 19, 2000

Sir:

This is a request for filing a new PATENT APPLICATION under Rule 53(b) entitled:  
POWDER COATED GENERATOR FIELD COILS AND RELATED METHOD  
without a filing fee and/or without an executed inventor's oath/declaration.  
This application is made by the below identified inventor(s). Attached hereto are the following papers:

- ☒ An abstract together with  
7 pages of specification and claims including  
17 numbered claims and also attached is/are  
2 sheets of accompanying drawings.  
☐ This application is based on the following prior foreign application(s):

Application No.	Country	Filing Date
-----------------	---------	-------------

respectively, the entire content of which is hereby incorporated by reference in this application, and priority is hereby claimed therefrom.

- ☐ This application is based on the following prior provisional application(s):
- | Application No. | Filing Date |
|-----------------|-------------|
|-----------------|-------------|

respectively, the entire content of which is hereby incorporated by reference in this application, and priority is hereby claimed therefrom.

Certified copy/ies of foreign applications attached.

This application is a ☐ continuation/☐ division/☐ continuation-in-part of application Serial No. , filed .  
Please amend the specification by inserting before the first line: --This application is a ☐ continuation/☐ division/☐ continuation-in-part of application Serial No. , filed , the entire content of which is hereby incorporated by reference in this application.--

Please amend the specification by inserting before the first line: --This is a continuation of PCT application No. , filed , the entire content of which is hereby incorporated by reference in this application.--

Please amend the specification by inserting before the first line: --This application claims the benefit of U.S. Provisional Application No. , filed , the entire content of which is hereby incorporated by reference in this application.--

Preliminary amendment to claims (attached hereto), to be entered before calculation of the fee.  
Also attached.

Inventor:	Patricia	C.	Irwin	USA
	(first)	MI	(last)	(citizenship)
Residence: (city)	Altamont	(state/country)		New York
Post Office Address:	1097 Knox Cave Road, Altamont, New York			
(Zip Code)	12009			

2. Inventor:	Peter	J.	Foley	USA
	(first)	MI	(last)	(citizenship)
Residence: (city)	Scotia	(state/country)		New York
Post Office Address:	3 Herrick Drive, Scotia, New York			
(Zip Code)	12302			

NOTE: FOR ADDITIONAL INVENTORS, check box ☒ and attach sheet with same information.

Address all future communications to NIXON & VANDERHYE P.C., 1100 North Glebe Road, 8<sup>th</sup> Floor, Arlington, Virginia 22201.

1100 North Glebe Road, 8<sup>th</sup> Floor  
Arlington, Virginia 22201-4714  
Telephone: (703) 816-4000  
Facsimile: (703) 816-4100  
MJK:ljb

NIXON & VANDERHYE P.C.

By Atty: Michael J. Keenan, Reg. No. 32,106

Signature: Michael J. Keenan



## POWDER COATED GENERATOR FIELD COILS AND RELATED METHOD

## BACKGROUND OF THE INVENTION

This invention relates to the manufacture of generator electromagnetic rotors, primarily for use in power generating equipment.

5           In conventional processes for manufacturing generator electromagnetic rotors, the current-carrying copper coils (called "field coils") are laboriously hand insulated. Each coil must be insulated from other coils, and the entire coil package must be insulated from the steel of the rotor. Significant cost savings and productivity improvements could be realized with  
10           a simpler and faster insulation system.

## SUMMARY OF THE INVENTION

          It is now proposed to coat the copper field coils with a suitable powder resin. The coating can be applied by electrostatic spraying or other suitable process. In one technique, the field coils remain stationary while electrostatic  
15           spray guns revolve around the coils. In an alternative technique, the coils are carried along a conveyor through a power spray booth. With either technique, the resin powder can be cured onto the field coils using resistance heating, induction heating, convection heating or infrared heating. Two coats of the resin powder are required to ensure complete coverage. In addition, and  
20           depending on the coil configuration, the ends of the copper bars may be masked to prevent powder coverage where not desired (for example, at the site of the electrical connections).

          Three classes of powder resins have the greatest potential for success in this particular application. They are epoxy powder coating resins, silicone  
25           powder coatings and hybrid systems of silicones/epoxies and silicones/acrylics. These materials have been shown to have high dielectric

strength, impact strength, thermal stability, flexibility, chemical resistance and adhesion.

Thus, in accordance with its broader aspects, the present invention relates to a field coil for an electromagnetic rotor comprising multiple  
5 windings, each substantially entirely coated with a powder resin having a dielectric strength of at least in the range of 1000-1500 v/mil.

In another aspect, the winding relates to a field coil for an electromagnetic rotor comprising a field coil substantially entirely coated with a powder resin selected from a group consisting essentially of epoxy powder  
10 resins and silicone powder resins.

In another aspect, the invention provides a method of insulating a field coil for an electromagnetic generator comprising:

- a. providing field coils comprising multiple layers of copper bars;
- b. coating the multiple layers of the field coil with a powder resin  
15 having a dielectric strength of at least about 1000-1500 v/mil.; and
- c. curing the powder resin.

#### BRIEF DESCRIPTION OF THE DRAWINGS

FIGURE 1 is a partial perspective view of a known field coil configuration; and

20 FIGURE 2 is a flow diagram of a field coil coating process in accordance with this invention.

## DETAILED DESCRIPTION OF THE INVENTION

With reference to Figure 1, a copper field coil 10 is shown that is of the helical wound type, with multiple layers or windings 12 formed from a single copper bar. The longitudinal sides 14, 16 of the windings are received within radial slots in the rotor body, while the ends 18, 20 of the windings project beyond the slots. In an alternative coil construction, each layer is comprised of a single winding or bar, the windings ultimately secured together in a stacked arrangement within the rotor slots. The present invention is equally applicable to either field coil construction.

- 10 The invention here relates to the elimination of known wrap-type insulation in favor of a powder resin coating. In an exemplary embodiment, two coats of a suitable resin powder coating are applied to the field coil 10. Prior to coating, the coil ends where the electrical connectors are located, are masked off, one such connector shown at 22. The masking can be done with
- 15 Teflon® sleeves or other suitable means.

Three classes of powder resins are preferred as coating compositions for the field coils. They include epoxy powder resins, silicone powder, and silicone hybrid resin systems (silicone/epoxies and silicones/acrylics). Examples are provided in Table I below.

TABLE I

	<i>Material</i>	<i>Dielectric Strength, v/mil</i>	<i>Impact Strength, inlb</i>	<i>Thermal Stability, use temp.</i>	<i>Flexibility, mandrel bend test</i>	<i>Chemical Resistance</i>	<i>Adhesion</i>
1.)	134 Epoxy	1000	>200 direct	155C	Passes ¼" mandrel	H <sub>2</sub> S, salt water	Good
2.)	5555 Epoxy	1100	>200 direct	180C	Passes ¼" mandrel	Oils and hydrocarbons	Good
3.)	5230 Epoxy	1100	>160 direct	155C	Passes ¼" mandrel	Oils and hydrocarbons	Good
4.)	5388 Epoxy	1200	>160 direct	180C	Passes ¼" mandrel	Oils and hydrocarbons	Good
5.)	Silicone	>1000	>160 direct	300C	Passes ¼" mandrel	Unknown	Fair
6.)	Silicone hybrid	1500	>220 direct	220C	Passes ¼" mandrel	Oils	Good

The epoxy powder compositions (items 1-4) are commercially available from 3M Corporation. The silicone powder coating composition (item 5) is a generic name and is currently less preferred. The Silicone hybrid (item 6) is commercially available from Crosslink Powder Coatings, Inc.

The compositions, particularly compositions 1-4 have high dielectric strength, impact strength, thermal stability, flexibility, chemical resistance and adhesion. The dielectric strength and thermal stability are critical factors, but chemical resistance and adhesion are important as well. The invention also contemplates modification of the base compositions through the addition of inorganic fillers that can enhance the properties of the final product, e.g., increased thermal conductivity of the coated copper bar and corona resistance of the coating.

Turning to Figure 2, a layout is schematically illustrated by which the coating process can be implemented.

This arrangement includes, generally, loading/unloading station 24; a powder coating station or booth 26; a curing oven 28; and an inverting station 30.

Coils to be coated may be moved by a suitable conveyor (not shown) to the loading/unloading station 24 where they are mounted, in succession, on suitable racks (one shown in Figure 1 at 32). Each rack 32 is carried along a first circuit or track 34 to a main track or circuit 36 at switch point 38, and the coil is moved by conveyor, overhead tram or other suitable means, to the powder coating station or booth 26. After coating, the coil is moved along the track 36 to the curing oven 28 where the coating is cured by resistance heating, induction heating, convection heating or by infrared heating. Once cured, the coil is moved along track 36 to a switch point 40 where the rack 32 and coil 10 are moved to an extension track 42. At the inverting station 30, the coil 10 is removed from the rack 32, inverted, and placed back on the rack. This inversion of the coil insures that the part of the coil not contacted by the coating composition, i.e., that part of the end 16 of the coil that rests on the rack 32, will be coated. Subsequently, the rack with the inverted coil rejoins the main track or circuit 36 for travel through the powder coating station 24 where a second coat is applied. The rack and coil continue to the curing oven 26 before switching back to the track 34 at switch point 40 for removal of the coil from the rack 32 and transfer to a conveyor (not shown). The construction of the powder spray booth 26, curing oven 28, and inverting station 30 transfer or switch mechanisms at switch points 38, 40 are all within the skill of the art.

While the invention has been described in connection with what is presently considered to be the most practical and preferred embodiment, it is to be understood that the invention is not to be limited to the disclosed embodiment, but on the contrary, is intended to cover various modifications and equivalent arrangements included within the spirit and scope of the appended claims.

WHAT IS CLAIMED IS:

1. A field coil for an electromagnetic rotor comprising multiple windings, each substantially entirely coated with a powder resin having a dielectric strength of at least in the range of 1000-1500 v/mil.

5           2. The field coil of claim 1 wherein said powder resin has a thermal stability in the range of at least 155-220° C.

3. The field coil of claim 1 wherein an electrical connector portions of the field coil are not coated.

10           4. The field coil of claim 1 wherein said field coil comprises a single wound member, having multiple layers, each layer coated on opposite sides with said powder resin.

5. The field coil of claim 1 wherein said field coil comprises plural layers of discrete coil members, each member being coated on opposite sides with said powder resin.

15           6. The field coil of claim 1 wherein said powder resin comprises an epoxy powder resin.

7. The field coil of claim 1 wherein said powder resin comprises a silicone hybrid powder resin.

20           8. The field coil of claim 1 wherein said field coil has two coats of said powder resin coating applied thereto.

9. A field coil for an electromagnetic rotor comprising a field coil substantially entirely coated with a powder resin selected from a group consisting essentially of epoxy powder resins and silicone powder resins.

10. A method of insulating a field coil for an electromagnetic rotor comprising:

a) providing a field coil comprising multiple layers of copper bars;

b) coating the multiple layers of the field coil with a powder resin

5 having a dielectric strength of at least about 1000-1500 v/mil.; and

c) curing the powder resin.

11. The method of claim 10 including masking an electrical connector of said field coil prior to step b).

10 12. The method of claim 10 wherein step b) comprises applying two coats of said powder resin.

13. The method of claim 10 wherein said powder resin comprises an epoxy powder resin.

14. The method of claim 10 wherein said powder resin comprises a silicone hybrid powder resin.

15 15. The method of claim 10 wherein step c is carried out by resistance heating, induction heating, convection heating or infrared heating.

16. The method of claim 12 wherein said field coil is inverted prior to application of a second coat.


20 17. The method of claim 10 wherein said coil is supported on a rack during steps b) and c) and wherein after step c), the field coil is removed from the rack, inverted, and re-placed on the rack; and subsequently, a second coat is applied to said field coil.




## POWDER COATED GENERATOR FIELD COILS AND METHOD OF MANUFACTURE

### ABSTRACT OF THE DISCLOSURE

5 A field coil for an electromagnetic rotor comprising multiple windings,  
each substantially entirely coated with a powder resin having a dielectric  
strength of at least in the range of 1000-1500 v/mil. A method of  
manufacturing a field coil for an electromagnetic rotor includes the steps of a)  
providing a field coil comprising multiple layers of copper bars; b) coating the  
multiple layers of the field coil with a powder resin having a dielectric strength  
10 of at least about 1000-1500 v/mil.; and c) curing the powder resin.





**Fig. 2**